

Inorganic Zinc Silicate

PRODUCT DESCRIPTION

A two pack, heat resistant zinc silicate shop (pre-construction) primer providing good corrosion protection (even after heating up to 1472°F (800°C)), with minimum production of zinc salts. Suitable for high speed welding and cutting with excellent resistance to damage caused by welding, gas cutting and fairing thereby reducing secondary surface preparation requirements in comparison to typical zinc silicate products.

INTENDED USES

As a shop (pre-construction) primer for the protection of steel during fabrication and assembly.

Suitable for use with controlled cathodic protection.

Suitable for use in new construction situations.

PRACTICAL INFORMATION FOR INTERPLATE 997

Color	Grey, Blue, Green, Red, Sand
Gloss Level	Matte
Volume Solids	25%
Typical Thickness	0.5-0.7 mils (13-18 microns) dry equivalent to 2.1-2.9 mils (52-72 microns) wet
Theoretical Coverage	16.70 m ² /liter at 15 microns d.f.t and stated volume solids 679 sq.ft/US gallon at 0.5 mils d.f.t and stated volume solids.
Practical Coverage	Allow appropriate loss factors
Method of Application	Automatic Airless Spray, Air Spray, Brush, Roller
Drying Time	

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			Minimum	Maximum
77°F (25°C)	¹	5 minutes	7 days	Extended ²
104°F (40°C)	¹	4 minutes	7 days	Extended ²

¹ Not applicable; Interplate 997 dries so quickly that this cannot be measured.

² See International Protective Coatings Definitions & Abbreviations

REGULATORY DATA Flash Point (Typical) Part A 41°F (5°C); Part B 50°F (10°C); Mixed 57°F (14°C)

For products used in North America, see Product Characteristics section.

Product Weight 11.7 lb/gal (1.40 kg/l)

VOC 5.30 lb/gal (636 g/l)
475 g/kg

EPA Method 24
EU Solvent Emissions Directive
(Council Directive 1999/13/EC)

Protective Coatings

Inorganic Zinc Silicate

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

Abrasive blast clean to SSPC SP10 or Sa2½ (ISO 8501-1:2007). If oxidation has occurred between blasting and application of Interplate 997, the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process, should be ground, filled, or treated in the appropriate manner.

If shot is used as the blasting media, it is preferable to add a minimum of 20 percent steel grit to the abrasive mixture in order to provide some angular profile in the substrate.

Remove all dust and abrasive via a suitable method prior to application of Interplate 997.

A surface profile of 1.2-3.0 mils (30-75 microns) is recommended.

APPLICATION

Mixing	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied.			
	(1)	Agitate Paste (Part A) with power agitator.		
	(2)	Slowly add Binder (Part B) to Paste while agitating and allow to mix for at least 5 minutes.		
	(3)	Strain material through a 30-60 mesh screen into an air agitator equipped tank, container or pressure pot.		
	(4)	Operate air agitator at low speed (~20rpm) to maintain an homogeneous mixture.		
	(5)	Keep system closed and free from moisture.		
Mix Ratio	0.5 part(s) : 1.0 part(s) by volume			
Working Pot Life	41°F (5°C)	50°F (10°C)	77°F (25°C)	104°F (40°C)
	24 hours	24 hours	24 hours	6 hours
Airless Spray	Recommended	Tip Range 19-23 thou (0.48-0.58 mm) Total output fluid pressure at spray tip not less than 853 psi (60 kg/cm²)		
Air Spray (Conventional)	Use suitable proprietary equipment..	Thinning may be required.		
Brush	Suitable - Small areas only.			
Roller	Suitable - Small areas only.			
Thinner	International GTA820 or International GTA840	Do not thin more than allowed by local environmental legislation		
Cleaner	International GTA820 or International GTA840			
Work Stoppages	Do not allow material to remain in hoses, guns or spray equipment. Thoroughly flush all equipment with International GTA820 or International GTA840. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
Clean Up	Clean all equipment immediately after use with International GTA820 or International GTA840. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.			
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

Inorganic Zinc Silicate

PRODUCT

Interplate 997 is designed for use in an automatic plant. It can be applied by manual spray but this is not recommended for complex structures.

CHARACTERISTICS

Above 1.2 mils (30 microns) DFT the level of weld fume and weld porosity will increase. Drying times will depend on the substrate temperature and on ventilation. Drying will also be retarded if the relative humidity is below 50%.

When applying Interplate 997 by brush or roller, it may be necessary to apply multiple coats to achieve the required film build.

Shop primers are not recommended for use as touch-up primers after fabrication.

Surface temperature must always be a minimum of 5°F (3°C) above dew point.

This product has the following specification approvals:

- Weld Fumes - Trace Gas Measurement during Welding (SLV)
- Weld Fumes - Thermal Degradation on Welding (NOHA)
- Weld Quality - Approved for Overweldable Shop Primers (GL)
- Weld Quality - Approval of Prefabrication Primers (LR)
- Weld Quality - Shop Primers for Welded Steel Structures (BV)
- Weld Quality - Shop Primers for Corrosion Protection of Steel Plates and Structures (DNV)
- Weld Quality - Russian Maritime Register of Shipping
- Fire Resistance - Marine Equipment Directive compliant

Product produced and supplied in North America has flash points of: Part A 60°F (15°C), Part B 61°F (16°C) and Mixed 60°F (15°C) due to locally sourced solvents. There is no detrimental effect on product performance.

SYSTEMS COMPATIBILITY

The following primers/topcoats are recommended for Interplate 997:

Intercure 200HS
Intergard 251
Intergard 269
Intergard 345
Intergard 475HS
Interseal 670HS
Interzinc 315
Interzinc 52

For other suitable primers/topcoats, consult International Protective Coatings.

Inorganic Zinc Silicate

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A	Part B		
		Vol	Pack	Vol	Pack
	20 liter	6.67 liter	20 liter	13.33 liter	15 liter
	5 US gal	1.67 US gal	5 US gal	3.33 US gal	3.5 US gal
For availability of other pack sizes contact International Protective Coatings					
SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A	Part B		
	20 liter	17.89 kg	12.78 kg		
	5 US gal	37.5 lb	29.2 lb		
STORAGE	Shelf Life	Part A: 12 months minimum at 77°F (25°C). Part B: 6 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

Disclaimer

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 2/5/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com